

folded

mutina + raw edges

folded textures

minifolded

midifolded




maxifolded

3 pattern miscelati random nella scatola
3 patterns randomly mixed into the box

[] folded sizes


design Raw Edges 2010
production industrial
material gres porcellanato non smaltato ad impasto omogeneo
unglazed homogeneous porcelain stoneware

thickness 10
*misure nominali - nominal sizes



3 pattern miscelati random nella scatola
3 patterns randomly mixed into the box

complementary pieces



3,8 · 60
*2" · 23 5/8"
battiscopa - skirting

V1
variazione uniforme
uniform variation

[] folded technical features/packing

| norma standard | caratteristiche features | valore prescritto value required | folded |
|-----------------------|--|--|---|
| ISO 10545/2 | DIMENSIONI - SIZES lunghezza e larghezza - length and width spessore - thickness rettilineità degli spigoli - straightness of edges ortogonalità - wedging planarità - flatness | ± 0,6% ± 5% ± 0,5% ± 0,6% ± 0,2% ± 0,5% | ± 0,15% ± 5% ± 0,10% ± 0,2% ± 0,25% |
| ISO 10545/3 | assorbimento d'acqua water absorption | <0,5% | 0,5% |
| ASTM C373 | | <0,5% | 0,5% |
| EN 101 | durezza superficiale (scala mohs) surface hardness (scala mohs) | > 5 | 7 |
| ISO 10545/9 | resistenza agli sbalzi termici resistance to thermal shock | nessuna alterazione visibile no visible alteration | resiste resistant |
| ASTM C484 | | no samples must show visible defects | unaffected |
| ISO 10545/12 | resistenza al gelo frost resistance | nessuna alterazione visibile no visible alteration | resiste resistant |
| ASTM C1026 | | unaffected | unaffected |
| ISO 10545/13 | resistenza agli attacchi chimici resistance to chemical attacks | nessuna alterazione visibile no visible alteration | resiste resistant |
| ASTM C650 | | | unaffected |
| ISO 10545/4 | resistenza alla flessione breaking strength | ≥35 N/mm ² | 61,2 N/mm ² |
| DIN 51130 - 04 | | valori medi 6° ÷ 10° 10° ÷ 19° 19° ÷ 27° | R9 R10 R11 R9 |
| ASTM C1028 | scivolosità anti-slip | > 0,60 | dry 0,78 wet 0,60 |
| ISO 10545/14 | resistenza alle macchie stains resistance | ≥ classe 3 | 4 |

| formato size | pz-mq pcs-sqm | pz-scat. pcs-box | mq-scat. sqm-box | scat.-pal. box-pal. | kg-scat. kg-box | kg-pal. kg-pal. | mq-pal sqms-pal |
|-------------------|------------------|---------------------|---------------------|------------------------|--------------------|--------------------|--------------------|
| 60-60 | 2,77 | 3 | 1,08 | 40 | 25,27 | 1020 | 43,20 |
| battiscopa 3,8-60 | - | 30 | 18 ml | 72 | 15,20 | 1095 | 1285 ml |



CERAMICHE
&
DESIGN

CERAMICHE
MUTINA SRL
Via Ghiarola Nuova 16
41042 Fiorano MO
Italia
+ 39 0536 812800 T
+ 39 0536 812808 F
mutina.it